



OPEN

Cost effective liquid phase exfoliation of MoS_2 nanosheets and photocatalytic activity for wastewater treatment enforced by visible light

Dhirendra Sahoo¹, Birendra Kumar², Jaivardhan Singh³, Subhasis Ghosh²,
Susanta Sinha Roy¹ & Bhaskar Kaviraj¹✉

Scalable production of high-quality MoS_2 nanosheets remains challenging for industrial applications and research in basic sciences. *N*-methyl-2-pyrrolidone (NMP) is a commonly used solvent for exfoliation of MoS_2 nanosheets having further disadvantage of slow volatility rate. The present study demonstrates a cost-effective facile chemical route to synthesize few-layer MoS_2 nanosheets using acetone as a solvent and by varying the initial concentration of samples to scale up the production in large scale to fulfill the demand for potential applications. In our study, we aim to obtain stable growth of high quality few-layer MoS_2 nanosheets by long sonication times. Optical absorption spectra, Raman spectra, size of nanosheets and layer thickness of as-grown MoS_2 nanosheets were found to be matching with those obtained from other synthesis methods. Effective photocatalytic performance of MoS_2 nanosheets without being consumed as a reactant was experimented by decomposing Methylene Blue dye in aqueous solution under irradiation of visible light. This study provides an idea to synthesize low-cost, sustainable and efficient photocatalytic material in large scale for the next generation to control water pollution quite efficiently by protecting the environment from the contamination coming from these dyes.

Since last decade, MX_2 based layered transition metal dichalcogenides (TMDs), where M (=Mo, W etc.) is a transition metal of group VI and X (=S, Se etc.) is a chalcogen, received much attention in science and technology due to their unique electrical, optical and mechanical properties. In bulk form, MoS_2 behaves as an indirect bandgap semiconductor. But with reduction of layers into few layers, bilayers, even monolayer, its bandgap becomes a direct one. In the MoS_2 crystal structure, the transition metal Mo is sandwiched between two hexagonal planes of chalcogen atom (S). In layered MoS_2 structure, there is a strong covalent bonding between each S-Mo-S trilayer and each MoS_2 layer is bonded to nearby layers by weak van der Waals (vdW) interaction between adjoining S-S layers (shown in Fig. 1b). During exfoliation, weak vdW forces start getting weaker, helping in thinning the layers (shown in Fig. 1a). The side view and top view of MoS_2 monolayer are drawn in Fig. 1c, d, where 'a' and 'b' on the image are the primitive lattice vectors of MoS_2 . The drastic changes in bandgap from near infrared to the visible range (bulk MoS_2 has an indirect band gap ~ 1.23 eV and the band gap rises up to ~ 1.9 eV after reduction of layers up to monolayer by exfoliation) opens abundant scope for this material in energy variable photovoltaic and optoelectronic applications, photocatalysis, electronic and electrochemical storage devices^{1–4}. Drastic enhancement (or modification) of band gap can be achieved by the following processes: (1) thinning of layers by exfoliation (2) bending or stretching of the substrate or choosing a substrate with minimum lattice mismatch (the lattice constant in a crystal changes with increase or decrease of temperature and pressure) (3) doping with certain amount of impurities or creating disorder in the crystal (4) changing the composition of

¹Department of Physics, School of Natural Sciences, Shiv Nadar University, NH91, Gautam Budh Nagar, Uttar Pradesh, Greater Noida 201314, India. ²School of Physical Sciences, Jawaharlal Nehru University, New Delhi 110067, India. ³Department of Physics and Nanotechnology, SRM Institute of Science and Technology, Kattankulathur, Kancheepuram 603203, India. ✉email: bhaskar.kaviraj@snu.edu.in




Figure 1. Synthesis and crystal structure of nanosheets. (a) Schematic illustration of synthesis process of MoS_2 nanosheets (designed by the author) (b) crystal structure of MoS_2 made by VESTA from X-ray diffraction results (c) side view and (d) top view of MoS_2 monolayer (sketched by VESTA software).

material and (5) quantum size effect (due to reduction of particle size)⁵. To this date, production of high quality, lofty yield, very thin and large area MoS_2 film remains challenging. Chemical vapor deposition (CVD) and physical vapor deposition (PVD) are preferred techniques to produce large area and high quality thin MoS_2 films for fabrication of electronic devices⁶. For electrochemical storage, catalysis and sensing applications films grown by liquid phase exfoliation are mostly preferred. Liquid phase exfoliation technique is one of the productive growth processes to get the highest yield MoS_2 by taking bulk MoS_2 as a precursor material. Lithium ion intercalation is also a widely used technique to produce thin films of MoS_2 with high yield. However, the limitations of such type of growth technique are: Lithium-ion source is itself flammable and solvents used for synthesis are harmful and explosive. That is why the synthesis should be carried out in an inert environment and a long time is needed for exfoliation just after the end of intercalation of ions into the gap of the layered material. However, experimental studies show clear evidence that bulk MoS_2 undergoes a structural transformation from the semiconducting 2H to the octahedral metallic or semi-metallic 1T structure in response to Li intercalation. Similarly sonication without the addition of surfactant gives a good yield but after filtering the surfactant the layers start to restack⁷⁻⁹.

So far liquid phase exfoliation (LPE) in an ultrasonic bath (with an appropriate solvent and mechanical force) has been able to draw attention for production of MoS_2 nanosheets with the highest efficiency. In addition, this technique is cost-effective, eco-friendly and free from contamination. The layers are peeled from bulk material by sonication for long time duration. The combination between the selection of solvent and concentration of solute decides the layer thickness of MoS_2 nanosheets. Earlier it has been reported that organic solvents like *N*-methylpyrrolidone (NMP), Isopropyl alcohol (IPA), ethanol, gives a good yield and highly populated nanosheets. However, the problem comes during transferring this exfoliated MoS_2 onto the substrate in case of high boiling point solvents like NMP (Boiling Point 202 °C). From the real application point of view, low boiling point organic solvents are preferred over high boiling point ones. In addition to that, surface tension component of solvent should match with that of MoS_2 . Still, many reaction parameters are to be calibrated to synthesize high-quality MoS_2 flakes by sonication and a lot of effort is required to enhance the quality production of exfoliated MoS_2 to fulfill the desired application. Complete removal of solvent stress is essential when we are coating the exfoliated MoS_2 on the substrate, which is ideal for application in sensors and electrochemical storage devices^{10,11}.

Still, the interaction of solvent-2D materials is under investigation, though LPE is the easiest and effortless route for the synthesis of MoS_2 in vast scale. For excellent LPE, the variation of the surface energy of MoS_2 and solvent should be minimum. In addition, the criteria to choose a good solvent for LPE are (1) for any concentration of 2D material, it should have the ability to exfoliate energetically, and (2) after exfoliation, the dispersed particle should be stable inside the solvent for a long time. However, from thermodynamic concept, surface tension is the key parameter to select a suitable solvent for LPE, but still, there are few reports of this problem. The intermolecular attraction between solid surface and solvent drop is the cause of surface tension and the difference




Figure 2. (a) UV-VIS spectrum of as-prepared MoS₂ nanosheets dispersion in acetone prepared with different initial concentration of bulk sample indicated in legend (b) estimated optical bandgap for MoS₂ nanosheets.

of surface tension create Gibbs free energy change during exfoliation. For efficient LPE and large-scale synthesis, the change of Gibbs free energy (ΔG) should be minimum^{12,13}.

In our work, we intend to study the role of the concentration of MoS₂ during LPE by keeping other growth parameters fixed. To overcome the limitation of NMP, we chose to utilize the solvent having room temperature volatility for exfoliation. The solvent used is acetone due to its low boiling point, low toxicity, surface tension energy (25.20 mJ/m² at 20 °C) and easy availability. This facilitates to extract MoS₂ nanosheets from the dispersion at the end of the exfoliation process. We synthesized nanosheets of MoS₂ prepared in different bulk initial concentrations of 0.08 mg/ml, 0.12 mg/ml, 0.3 mg/ml and 0.4 mg/ml by using an ultra-sonication bath. The results show that various parameters like sonication time, duration of centrifugation and amount of solvent indirectly influence the growth affirming that such small concentrations of bulk MoS₂ powder decide the size and thickness of nanosheets. Our study demonstrates that facile environment-friendly production of few-layer TMD nanosheets without the incorporation of any hazardous chemicals or severe synthesis conditions or any advanced/ household solvents.

Consequently, it has been studied that MoS₂ nanostructure shows the quantum size effects. The quantum size effect causes an increase in the bandgap of MoS₂ nanostructure significantly, driving to a variation in their redox potentials as well. Such relevant variation in the energy levels of the conduction and valence band edges enable MoS₂ nanosheets to act as an efficient photocatalytic agent in the presence of visible light¹⁴.

Photocatalytic activity of as-synthesized few-layer MoS₂ nanosheets was experimented by decomposing Methylene blue (MB) dye in aqueous solution under the irradiation of visible light. Methylene blue (C₁₆H₁₈N₃Cl) is a handy compound and has a broad range of industrial application in the field of medical, chemical, pharmaceutical and aquaculture. This dark green solid powder results in a blue colored solution having no odor after mixing with pure water. Various diseases can spread like mild bladder irritation, abdominal pain, nausea, stomach cramps, pain in frequent urination while bathing, washing or drinking or by eating food exposed to contaminated water. Semiconductor materials generally have absorption under sunlight commonly employed as self-cleaning material. TiO₂ is used as the self-cleaning material due to its low cost, wide bandgap (> 3 eV), good photocatalytic activity and high availability in the earth's crust. However, other semiconductors like ZnO, SnO₂, and ZrO₂ also show good photocatalytic activity under UV light irradiation^{15–17}.

The photocatalytic performance of the atomically thin 2H-MoS₂ nanosheets prepared from different concentrations were estimated by the degradation of methylene blue. It was found that the visible light response of MoS₂ nanosheets is strongly dependent on the layer numbers. It is observed that bilayer MoS₂ nanosheets prepared from 0.08 mg/ml bulk initial concentration shows maximum degradation as compared to other samples. Our work shows that as grown solid, stable and insoluble (to water and dilute acid) MoS₂ nanosheets prepared from this cost-effective synthesis approach can be used as promising future photocatalytic materials to control water pollution by degrading this hazardous compound such as MB under the irradiation of visible light instead of UV light.

Results and discussions

A dispersion of MoS₂ nanosheets prepared with different initial concentrations of bulk powder in acetone was characterized by UV-VIS-NIR spectroscopy (Fig. 2a, b). The exfoliated MoS₂ nanosheets as well as bulk MoS₂ show four excitonic peaks in the absorption spectra. These four peaks ("A and B" and "C and D") with an energy separation ~ 184 meV are due to the transition between the split-valence band and conduction band at the K-point and the M-point of Brillouin zone respectively. In the bulk sample, the energy splitting between different characteristic peaks emerges from spin-orbit interaction and interlayer coupling, but the interlayer coupling




Figure 3. X-ray diffraction pattern of pristine MoS_2 powder and nanosheets prepared with different initial concentration with a y-axis offset.

starts to diminish with reduction of layer number^{8,19}. Excitonic peaks are gradually blue shifted with decrease of initial concentration as compared to bulk MoS_2 excitonic spectra. The peak around 352 nm reveals the increase of optical bandgap with a decrease in thickness of MoS_2 nanosheets, which has the significance of indirect to direct band transition at the edge of the Brillouin zone. The indirect to direct band transition can be ascribed to the absence of interlayer coupling. The absorption spectra of exfoliated nanosheets progressively exhibited distinct peaks shift with decrease in initial MoS_2 concentration, which is the result of quantum confinement and significant size reduction phenomena in MoS_2 nanosheets²⁰. Finally, the weight of dispersed nanosheets were measured by weighing after drying and calculated from one batch of samples to be 1.13, 1.35, 1.58, and 2.07 mg.

The crystal structure of bulk MoS_2 and few-layered (FL) MoS_2 was orderly characterized by X-ray diffraction (XRD) technique (ICPDS-00-037-1492). As shown in Fig. 3, an apparent strong diffraction peak of bulk MoS_2 has been found at $2\theta = 14.4^\circ$ matching to the (002) plane²¹. This strong intense peak indicates that the pristine material has a large number of crystal planes oriented in that direction. MoS_2 nanosheets prepared with different initial concentration of bulk material show that the (002) peak of exfoliated material relatively decreases due to the absence of constructive interference from the crystal planes, which reveals that the bulk material was peeled to few layer. For the initial concentration 0.08 mg/ml, there is a very low intensity peak on the XRD patterns, indicating that exfoliated nanosheets are very thin. As a result, the reduction of the intensity of (002) plane signifies decrease of layer number in few-layered MoS_2 (FL- MoS_2)^{4,22,23}. Hence, the stacked structure along the c-axis and reduction of the particle size can be allocated to (002) diffraction peak. Basically, in 2H- MoS_2 crystal structure, the (002) plane describes the interference of layered S-Mo-S and it's periodical progression along the c-axis in 2H symmetry. Despite all diffraction peaks, there is another extra peak observed at $2\theta = 22.51^\circ$ in all samples, which is assigned to the diffraction peak of SiO_2/Si substrates.

Raman spectroscopy is commonly used to examine the molecular fingerprint of layered materials. Figure 4 displays the typical Raman spectra of bulk MoS_2 and exfoliated nanosheets prepared from varying initial concentration of pristine MoS_2 . Raman blue shift corresponds to gain of energy of scattered photons from materials, and the peak has shifted to higher wavenumber from its bulk value. Two distinct peaks are observed at $376.88\text{ cm}^{-1}(\text{E}_{2g}^1)$ and $403.39\text{ cm}^{-1}(\text{A}_{1g})$ for the bulk MoS_2 ²¹. The frequency difference between two noticeable peaks is $26.51/\text{cm}$. MoS_2 consists of two recognized phonon modes corresponding to E_{2g}^1 (in plane opposite vibrations of sulfur/molybdenum atoms) and A_{1g} (out-of-plane vibrations of sulfur atoms). As bulk MoS_2 becomes few layer nanosheets (in case of 0.08 mg/ml concentration), the in-plane mode upshifts to $\sim 383.22/\text{cm}$ and the out of plane upshifts to $405.297/\text{cm}$, the frequency difference between two phonon modes decreased from 26 to $22.07/\text{cm}$. This frequency difference $22.07/\text{cm}$ of the exfoliated nanosheets is comparable to bilayer. The corresponding difference of these frequency modes (Δk) is used to calculate the number of layers^{24,25}. It has been found from the Raman spectrum that nanosheets prepared with an initial concentration of 0.08 mg/ml shows the minimum frequency difference as compared to 0.12, 0.3 and 0.4 mg/ml.

The morphologies of as-synthesized MoS_2 nanosheets have been examined by scanning electron microscopy (SEM). Figure 5a-d shows the SEM images of the surface of exfoliated MoS_2 nanosheets. By imaging the thin




Figure 4. Raman spectrum of bulk MoS_2 and nanosheets prepared from different initial concentration of bulk MoS_2 powder.




Figure 5. SEM images of MoS_2 exfoliated nanosheets synthesized with different MoS_2 concentration (a) 0.4 mg/ml (b) 0.3 mg/ml (c) 0.12 mg/ml (d) 0.08 mg/ml.




Figure 6. TEM and high resolution TEM (HRTEM) images of MoS_2 nanosheets **(a, e)** 0.08 mg/ml **(b, f)** 0.12 mg/ml **(c, g)** 0.3 mg/ml **(d, h)** 0.4 mg/ml. Inset images in **(e-h)** show the corresponding electron diffraction pattern of nanosheets prepared from the bulk initial concentration 0.08–0.4 mg/ml.

MoS_2 films, we observed that the sheet size of MoS_2 sheets prepared from 0.4 mg/ml concentration (Fig. 5a) is irregular in a range of 300 nm to 1 μm , whereas MoS_2 nanosheet from 0.3, 0.12 and 0.08 mg/ml (Fig. 5b-d) shows comparative uniform sheets with a size range of 20 nm to 200 nm. The lateral dimension ordering of MoS_2 nanosheets decreases with decrease of bulk initial concentration. All exfoliated samples are spread up by the sheet-like structure with various orientations²⁶.

Figure 6a-d show transmission electron microscopy (TEM) images at low magnification and corresponding height distribution of as-synthesized MoS_2 nanosheets shown in Figure 6e-h where the measured height for various concentrations lies between 1.5 and 4.9 nm. The edge view of samples was focused at a small angle ($\sim 9^\circ$) to measure the height of nanosheets. The data reveals that thickness of nanosheets is comparable to 2–7 layer MoS_2 by assuming monolayer thickness to be 0.7 nm^{27,28}. It can be seen that the layer thickness increases with increase in MoS_2 bulk initial concentration. It has been found from X-ray diffraction results that, the projection of the (002) peak indicates the presence of well-stacked layered formations along the particular orientation. A similar trend was observed in TEM results and found that as-grown nanosheets are of a few-layer. Selective area electron diffraction (SAED) pattern in the inset of Fig. 6e-h reveal the in-plane hexagonal atomic arrangement in all samples prepared from different bulk initial concentrations.

Further optical properties were studied by photoluminescence (PL) spectroscopy, which is a highly sensitive tool and helpful technique to know the behavior of photo-induced electron–hole pairs, charge separation and charge recombination phenomena²⁹. The evolution of electronic and optical properties due to quantum confinement is relevant when the nanosheets are of adequately small size—typically in the order of nm or less². The bandgap of MoS_2 nanosheets increases from indirect to direct one as the size of the nanostructure decreases and these nano-sized MoS_2 exhibit excellent photoluminescence properties¹⁸. But, their optical absorption and emission can be attuned through the quantum size effect. The PL emission spectra of MoS_2 nanosheets (prepared from initial concentrations of bulk MoS_2) under different excitation wavelengths varying from 330 to 560 nm were investigated and shown in Fig. 7. A strong emission peak is observed at 413 nm under an excitation wavelength of 330 nm, while the intensity of emission spectra gradually decreased and redshifted with the increase of excitation wavelength. The emission spectra at 649 nm starts to disappear under the excitation wavelength of 560 nm for all concentrations. Most of the emission spectra were recorded in the blue color regime. Herein, the excitation-dependent PL measurements confirmed the poly-dispersive nature of MoS_2 suspension³⁰. The resulting emission of the PL spectrum is a result of excitation recombination at the electron (hole) trap created by the uncompensated positive (negative) charge at the dangling bond from as-grown MoS_2 nanosheets. To know the origin of the PL spectrum under the excitation wavelength of 560 nm (inset of Fig. 7a, b), we can show the correspondence with absorbance spectra in the photon energy range 1.3–3.7 eV (shown in Fig. 2b). The PL peak at 1.91 eV in both the samples (0.08 and 0.12 mg/ml) is exactly matching with “A” peak of absorbance spectra (shown in Fig. 2b). This direct band gap transition promises use of this material as a good photocatalytic agent in range of visible wavelengths^{31–34,43}.

The economic growth across the world requires the treatment of wastewater and to make it reuse. Therefore, several safe purification methodologies such as photocatalysis and biodegradation have been implemented to




Figure 7. PL emission spectra of as-prepared MoS₂ nanosheets of various concentration (a) 0.08 mg/ml (b) 0.12 mg/ml (c) 0.3 mg/ml and (d) 0.4 mg/ml under different excitation wavelength ranging from 330 to 560 nm.

mal water free from pollutants. However, photocatalysis has numerous advantages like its environmental safety, absence of malignant byproduct and performs under the irradiation of visible light. Photocatalytic activity of MoS₂ nanosheets was investigated by degradation of Methylene blue (MB) dye under irradiation of visible light. Apart from slow recombination of electron–hole pairs, the strong light absorption is also an outstanding requirement for the highly productive photocatalyst. To investigate the mechanism of improved visible light adsorption, we have to perform UV–Vis spectroscopy measurement. Figure 8a–d show the time-dependent decomposition of MB dye under visible light irradiation. In dark, MB reduction happens due to adsorption of MoS₂ inside the solution. Absorbance peak of 665 nm was considered to track the percentage of degradation of the dye in the solution. But, in the presence of visible light irradiation, nanosheets prepared from 0.08 mg/ml show degradation of dye (45.6%) is faster as compared to the dark after 1 h. Both samples prepared from 0.12 and 0.3 mg/ml show 32.3 and 31.1% degradation of dye respectively and the percentage of degradation decreases gradually (upto 27%) in case of nanosheets synthesized from 0.4 mg/ml. The percentage of degradation of dye was found maximum in case of nanosheets prepared from 0.08 mg/ml and gradually decreased with increase of layer numbers, which was shown in Fig. 8. In the case of the sample prepared from 0.08 mg/ml, around 85% of degradation was observed after continuous irradiation of visible light for 12 h. Significant degradation of about 75% happens after 6 h light irradiation (shown in Fig. 9). In addition to this, it was observed that nearly 26% of degradation occurs due to physical adsorption on the surface MoS₂ after 12 h of dark treatment. The formula applied to estimate the percentage (%) of degradation is¹⁶

$$\text{Percentage of degradation of dye} = \frac{A_0 - A_t}{A_0} \times 100\% \quad (1)$$

where A₀ is the absorbance before irradiation and A_t is the absorbance after irradiation time 't'.




Figure 8. Photocatalytic response of exfoliated MoS₂ nanosheets prepared from various bulk initial concentrations.

The lower portion of the valence band is decided by the d-orbital of Mo and p-orbital of the S accompanied by d_z^2 , d_{xy} and $d_x^2 - y^2$ non-bonding orbitals at Mo. The formal charge of -2 for the sulfur provides a formal charge of $+4$ for Mo in MoS₂. The d_z^2 band is completely occupied and clearly revealing the semiconducting nature of MoS₂¹⁷. Excitation of an electron by visible light irradiation is not accessible from half-filled 4d orbitals of Mo in order to enhance the photocatalytic activity, because of, Mo 4d and S 3p states are most dominant orbitals of the VB maxima and CB minima in MoS₂. Overall, it has been found that as-synthesized MoS₂ nanosheets (having thickness 1.5–5.25 nm) show good photocatalytic behavior under irradiation of visible light rather than UV light^{31–34}. As the thickness decreases into the order of nanoscale, the energy gap increases gradually. The highest value of energy gap 1.91 eV is due to quantum confinement and size effect. Defects produced during synthesis gives rise to form multiple energy gap. The MoS₂ nanosheets having multiple energy gaps produce more electron–hole pairs with the incident of visible light. Formation of electron–hole pairs in MoS₂ nanosheets in the presence of visible light is an advanced oxidation process, in which excitation of electron happens from VB by absorbing a sufficient amount of light. Water molecules are adsorbed (lying on the top) at the MoS₂ surface in dark due to high available surface area. In MoS₂ nanosheets, photo-generated electron–hole pairs travel a shorter distance to take part in oxidation–reduction reaction before recombination to facilitate the photocatalytic activity. A series of chemical reactions between adsorbed H₂O, h⁺, e⁻ and hydroxyl radicals (OH) occur after irradiation of visible light. The quantum confinement and edge effect in thin MoS₂ nanosheets make notable changes in the active sites of valence and conduction band so that the oxidation potential is so high to generate more hydroxyl ions as correspond to O²⁻ ions. Although the oxidation potential of bulk MoS₂ is not so sufficient to generate more hydroxyl ions. The hydroxyl radicals are a strong oxidizing agent, which attacks and destroys all pollutants




Figure 9. Plot of percentage of degradation (%) vs duration of light irradiation.




Figure 10. Schematic of photo catalysis mechanism in MoS_2 under the irradiation of visible light.

present in water via various chemical reactions leading to form carbon dioxide and water as by-products, which is shown in Fig. 10. The degradation of the methylene blue is due to the photocatalytic activity via efficient charge separation in MoS_2 nanosheets having high mobility of charge carriers^{35–42,44}. A qualitative comparison of our work with other reported work has been mentioned in Table 1^{45–49}.

Conclusion

In conclusion, an easy, efficient, eco-friendly and contamination-free growth technique has been employed for scalable synthesis of 2–7 layers of 2H- MoS_2 nanosheets without the addition of any surfactants and the acetone used as a solvent for synthesis to overcome the drawback (i.e. low volatility) of extensively used organic solvents like NMP. So far, the listed suitable solvents are those, which have a less mismatch of surface energy at the solvent-solid interface for efficient synthesis of 2D materials. Incorporation of long sonication times and low concentrations of bulk powder allow for peeling off the layers and the dispersions to maintain good stability after 1 month.

S. no	Catalyst	Mass loading (mg)	Light source	Initial concentration	Reaction time (min)	Percentage of degradation (%)	References
1	Porous MoS ₂	20	100 W xenon lamp	10 mg/L	150	89.2	⁴⁹
2	MoS ₂ nanocrystals	25	150 W Xenon lamp	100 μ M	180	100	⁴⁹
3	MoS ₂ ultrathin nanosheets	10	400 W Asahi spectra (Xenon lamp)	100 mg/L	36	95.3	⁴⁹
4	Flower like spheres MoS ₂	40	150 W xenon lamp	10 mg/L	90	95.6	⁴⁹
5	MoS ₂ nano- flakes	20	Visible light	100 μ M	20	99.3	⁴⁹
6	MoS ₂ nanosheets	1	22 W B22 LED bulb	5 mg/L	60	45.6	
					720	85	This work

Table 1. Comparison between the photocatalytic performances of MoS₂ nanosheets and other nanostructure in the degradation of methylene blue dye under different light sources^{45–49}.

The photocatalytic activity of as-grown MoS₂ nanosheets for the degradation of MB dye under the irradiation of visible light has been checked, which permits to use this material for the cleaning of wastewater using sunlight. The long blue shifts reveal the appearance of a strong quantum confinement effect in our as-synthesized samples as compared to bulk. Due to this confinement, the band gaps of MoS₂ nanosheets arise and their redox potentials vary respectively. The ultrathin MoS₂ nanosheets help as an excelerate catalyst to enhance the photocatalytic activity by suppressing the recombination of photo excited electrons and holes.

Methods

Synthesis of nanosheets. The MoS₂ (Molybdenum (VI) sulfide) powder was purchased from Sigma Aldrich (product code: 69860) having particle size \sim 6 μ m (max. \sim 40 μ m); acetone was used as the solvent. All the chemicals used in the study were analytical grade and employed without further purification. Initiating from bulk MoS₂ powder, nanosheets were synthesized by the joint phenomena of sonication and centrifugation. A 30 mg of bulk MoS₂ powder was ground by hand using a mortar and pestle for 2 h. Then the powder was left to dry for 12 h in a vacuum oven at 200 °C to remove water content and impurity. Various concentration (0.08–0.4 mg/ml) of samples was prepared by mixing dried MoS₂ powder with 30 ml of acetone in glass vials and the neck of the vials was wrapped tightly by Parafilm. The suspension was then carried out to a high sonicating bath for sonication up to 30 h to interrupt the weak van der Waals forces between adjacent layers of bulk MoS₂. At last, the solution was centrifuged for 2 h at 1328 rcf by using NEYA 10 REMI centrifuge and the supernatant was collected by pipetting using a micropipette. Finally, the supernatant was filtered using a filtered system. The exfoliated refined MoS₂ nanosheets were drop casted above SiO₂/Si substrate and dried at 50 °C.

Characterization. SHIMADZU's spectrophotometer (UV-Vis 3700) was used to examine the absorption spectra of synthesized samples. The proper baseline correction was done by putting the identical cuvette filled with acetone at both source and reference site to extract the absorption/reflection from the cuvette and noise effect due to air and acetone solvent. To achieve a high concentration of MoS₂ nanosheets, low relative centrifugal force (1328 rcf) was fixed to separate exfoliated particles from an un-exfoliated part. The concentration of supernatants was calculated by drying the specific amount of solution in vacuum at 70 °C, the mass difference giving the idea about resultant concentration. Diffraction peaks were analyzed using a RigakuMiniflex diffractometer with typical X-ray tube (Cu K α radiation, 40 kV, 30 mA) and Hypix-400 MF 2D hybrid pixel array detector (HPAD). Structural analysis was conducted using a transmission electron microscope (TEM) (Model JEOL JEM-2100F) operated at accelerating voltage 200 kV. TEM analysis was made by dropcasting the diluted MoS₂ solution over the carbon-coated copper grid accompanied by drying. The microstructure of exfoliated nanosheets was studied by scanning electron microscope (VEGA3, TESCAN). The dispersed nanosheets were dropcasted onto a clean piece of sticky carbon tape, allowed to dry and put it onto SEM stub. The SEM images were collected by applying accelerating voltage 5 kV. The Raman spectra of the MoS₂ nanosheets was collected using a Renishaw Raman microscope using 532 nm (0.3 mW) laser, 10-s scans acquired with the laser using the 20 \times objective of an Olympus microscope. PL spectra were obtained with Fluoromax 4C Horiba Scientific spectrophotometer upon excitation of a series of wavelengths using 450 W Xenon lamp.

Photocatalytic activity measurement. In this work, 30 ml of 5 ppm of MB (methylene blue) was prepared to measure the photocatalytic activity of each sample. The samples were coated on the 1 \times 1 cm² Si/SiO₂ substrate and dried at 60 °C inside the vacuum furnace for overnight. The mass loading of 1 mg was maintained for each sample prepared from different concentrations. Each sample was immersed inside the MB dye for 60 minutes to attain absorption–desorption equilibrium in the dark. For irradiation, a 22 W Syska SRL based B22 LED bulb was used as a visible light source. The bulb was fixed inside one closed dark chamber and about 10 cm distance was maintained in between light source and sample. The samples inside the dye were exposed to visible light for 12 h. Then 3 ml of dye was taken out in the interval of 1 h from each sample and analyzed by UV-Vis absorption spectroscopy.

Received: 20 April 2019; Accepted: 1 June 2020
Published online: 01 July 2020

References

- Chhowalla, M. *et al.* The chemistry of two-dimensional layered transition metal dichalcogenide nanosheets. *Nat. Chem.* **5**, 263–275 (2013).
- Mak, K. F., Lee, C., Hone, J., Shan, J. & Heinz, T. F. Atomically thin MoS₂: A new direct-gap semiconductor. *Phys. Rev. Lett.* **105**(13), 136805 (2010).
- Yoffe, A. D. Layer compounds. *Annu. Rev. Mater. Sci.* **3**, 147–170. <https://doi.org/10.1146/annurev.ms.03.080173.001051> (1973).
- Liu, Y. *et al.* Layer-by-layer thinning of MoS₂ by plasma. *ACS Nano* **7**, 4202–4209 (2013).
- Onishi, T. *et al.* Quantum chemistry in functional inorganic materials. *Adv. Quantum Chem.* **64**, 31–81 (2012).
- Wang, H., Li, C., Fang, P., Zhang, Z. & Jhang, J. Z. Synthesis, properties and optoelectronic applications of two-dimensional MoS₂ and MoS₂-based heterostructure. *Chem. Soc. Rev.* **47**, 6101–6127 (2018).
- Jawaid, A. *et al.* Mechanism for liquid phase exfoliation of MoS₂. *Chem. Mater.* **28**, 337–348 (2016).
- Mason, T. J. & Lorimer, J. P. *Applied Sonochemistry: Uses of Power Ultrasound in Chemistry and Processing* (Wiley-VCH Verlag GmbH & Co. KGaA, New York, 2003).
- Xu, H., Zeiger, B. W. & Suslick, K. S. Sonochemical synthesis of nanomaterials. *Chem. Soc. Rev.* **42**(13), 2555–2567 (2013).
- Hanlon, D. *et al.* Production of molybdenum trioxide nanosheets by liquid exfoliation and their application in high-performance supercapacitors. *Chem. Mater.* **26**(4), 1751–1763. <https://doi.org/10.1021/cm500271u> (2014).
- Backes, C. *et al.* Functionalization of liquid-exfoliated two-dimensional 2H-MoS₂. *Angewandte Chemie.* **127**(9), 2676–2680. <https://doi.org/10.1002/ange.201409412> (2015).
- Smith, R. J. *et al.* Large-scale exfoliation of inorganic layered compounds in aqueous surfactant solution. *Adv. Mater.* **23**, 3944–3948 (2011).
- Miura, K. & Kamiya, S. Observation of the amontons-coulomb law on the nanoscale: frictional forces between MoS₂ flakes and MoS₂ surfaces. *EPL Europhys. Lett.* **58**, 610 (2002).
- Xiang, Q., Yu, J. & Jaroniec, M. Synergetic effect of MoS₂ and graphene as cocatalysts for enhanced photocatalytic H₂ production activity of TiO₂ nanoparticles. *J. Am. Chem. Soc.* **134**, 6575–6578 (2012).
- Marci, G. *et al.* Network structured SnO₂/ZnO heterojunction nanocatalyst with high photocatalytic activity. *J. Phys. Chem. B.* **105**, 1033 (2001).
- Paul, S. & Choudhury, A. Investigation of the optical property and photocatalytic activity of mixed phase nanocrystalline titanite. *Appl. Nanosci.* **4**, 839–847 (2014).
- Mattheiss, L. F. *et al.* Band structures of transition-metal-dichalcogenide layer compounds. *Phys. Rev. B* **8**(8), 3719–3740 (1973).
- Gopalakrishnan, D. *et al.* MoS₂ quantum Dot-interspersed Exfoliated nanosheets. *ACS Nano* **8**, 5297–5303 (2014).
- Nguyen, E. P. *et al.* Investigation of two-solvent grinding-assisted liquid phase exfoliation of layered MoS₂. *Chem. Mater.* **27**, 53–59 (2015).
- Pagona, G. *et al.* Exfoliated semiconducting 2H-MoS₂ and 2H-V₂S₂ assisted by cholsulfonic acid. *Chem. Commun.* **51**, 12950–12953 (2015).
- Lee, C. *et al.* Anomalous lattice vibrations of single- and few-layer MoS₂. *ACS Nano* **4**, 2695–2700 (2010).
- Kittel, C. *Introduction to Solid State Physics* (2, 38–39 (Wiley, New York, 1968).
- Xu, S., Li, D. & Wu, P. One-pot, facile, and versatile synthesis of monolayer MoS₂/WS₂ quantum dots as bio imaging probes and efficient electro catalysts for hydrogen evolution reaction. *Adv. Funct. Mater.* **25**, 1127–1136 (2015).
- Molina-Sánchez, A. & Wirth, J. Phonons in single-layer and few-layer MoS₂ and WS₂. *Phys. Rev. B*. <https://doi.org/10.1103/PhysRevB.84.155413> (2011).
- Li, H. *et al.* From bulk to monolayer MoS₂: Evolution of Raman scattering. *Adv. Funct. Mater.* **22**, 1385–1390 (2012).
- Zhu, M. Y. *et al.* A mechanism for carbon nanosheet formation. *Carbon* **45**, 2229–2234 (2007).
- Perea-López, N. *et al.* CVD-grown monolayer MoS₂ as an effective photo-sensor operating at low-voltage. *2D Mater.* **1**, 011004 (2014).
- Li, B. *et al.* Preparation of monolayer MoS₂ quantum dots using temporally shaped femtosecond laser ablation of bulk MoS₂ targets in water. *Sci. Rep.* **7**, 11152 (2017).
- Wang, Q. H., Kalantar-Zadeh, K., Kis, A., Coleman, J. N. & Strano, M. S. Electronics and optoelectronics of two-dimensional transition-metal dichalcogenides. *Nat. Nanotechnol.* **7**, 699–712 (2012).
- Štengl, V. & Hejzch, J. Strongly luminescent monolayered MoS₂ prepared by effective ultrasound exfoliation. *Nanoscale* **5**, 3387–3394 (2013).
- Shinde, L. B. & Pillai, V. K. Electrochemical preparation of luminescent graphene quantum dots from multiwalled carbon nanotubes. *Chem. Eur. J.* **18**, 12522–12528 (2012).
- Bao, L. *et al.* Electrochemical tuning of luminescent carbon nanodots: From preparation to luminescence mechanism. *Adv. Mater.* **23**, 5801–5806 (2011).
- Zhang, M. *et al.* Facile synthesis of water-soluble, highly fluorescent graphene quantum dots as a robust biological label for stem cells. *J. Mater. Chem.* **22**, 7461–7467 (2012).
- Khan, M. *et al.* Size-dependent quantization effect in optical properties of MoS₂ nanostructure. *Chemistryselect* **4**, 2116–2121 (2019).
- Coehoorn, R. *et al.* Electronic structure of MoSe₂, MoS₂, and WSe₂. I. Band-structure calculations and photoelectron spectroscopy. *Phys. Rev. B. Condens. Matter* **35**, 6195–6202 (1987).
- Paton, K. R. *et al.* Scalable production of large quantities of defect-free few-layer graphene by shear exfoliation in liquids. *Nat. Mater.* **13**(6), 624–630. <https://doi.org/10.1038/nmat3944> (2014) ((PMID: 24747780)).
- Norskov, J. K. *et al.* Trends in the exchange current for hydrogen evolution. *J. Electrochem. Soc.* **152**(3), 23–26 (2005).
- Vrubel, H. *et al.* Molybdenum boride and carbide catalyze hydrogen evolution in both acidic and basic solutions. *Angewandte Chemie Int. Edn.* **51**(15), 12703–12706 (2012).
- Chena, C. C. *et al.* Photocatalyzed N-deethylation and degradation of Brilliant Green in TiO₂ dispersions under UV irradiation. *Desalination* **219**, 89–100 (2008).
- Thakare, Y. D. & Jadhav, S. M. Degradation of Brilliant Green dye using cavitation based hybrid techniques. *Int. J. Adv. Eng. Technol.* **4**, 31–36 (2013).
- Gao, J. *et al.* Decoloration of aqueous Brilliant Green by using glow discharge electrolysis. *J. Hazard. Mater.* **B137**, 431–436 (2006).
- Munusamy, S., Aparna, R. S. L. & Prasad, R. G. S. V. Photocatalytic effect of TiO₂ and the effect of dopants on degradation of brilliant green. *Sustain. Chem. Process.* **1**, 4 (2013).
- Jin, W. *et al.* Direct measurement of the thickness dependent electronic band structure of MoS₂ using angle-resolved photoemission spectroscopy. *Phys. Rev. Lett.* **111**, 10680 (2013).
- Zong, X. *et al.* Photocatalytic H₂ evolution on MoS₂/CdS catalysts under visible light irradiation. *J. Phys. Chem. C.* **114**, 1963–1968 (2010).
- Zhou, Z. *et al.* Hydrothermal fabrication of porous MoS₂ and its visible light photocatalytic properties. *Mater. Lett.* **131**, 122 (2014).

46. Lin, L. *et al.* A photo-catalyst of Sulphur depleted monolayered molybdenum sulfide nanocrystals for dye degradation and hydrogen evolution reaction. *Nano Energy*. **38**, 544–552 (2017).
47. Abinaya, R. *et al.* Ultrathin layered MoS₂ nanosheets with rich active Sites for enhanced visible light photocatalytic activity. *RSC Adv.* **8**, 26664–26675 (2018).
48. Sheng, B. *et al.* Effects of excess sulfur source on the formation and photocatalytic properties of flower-like MoS₂ spheres by hydrothermal synthesis. *Mater. Lett.* **144**, 153 (2015).
49. Sadhanal, H. K. *et al.* Green synthesis of MoS₂nanoflowers for efficient degradation of methylene blue and crystal violet dyes under natural sun light conditions. *New J. Chem.* **42**, 14318–14324 (2018).

Acknowledgements

We acknowledge Shiv Nadar University for financial assistance during this work. We also thank Professor Subhash Ghosh for explaining us the basics of the experiment and Dr. Bhaskar Kaviraj for sketching the experimental problem. The authors would like to thank Dr. Jaivardhan Sinha at SRM Institute of Science and Technology for conducting Raman characterization, photoluminescence, and Dr. Rakesh Sharma at Shiv Nadar University for assisting in the XRD characterization.

Author contributions

D.S. imagined and designed the details of experimental plans. Experiment and characterization were handled by D.S., J.S. and B.K. D.S., S.G. and B.K. successfully did scientific discussion and result verification and D.S. wrote the paper with the assistance of B.K. S.S.R. helped in the discussion of photo catalysis results.

Competing interests

The authors declare no competing interests.

Additional information

Correspondence and requests for materials should be addressed to B.K.

Reprints and permissions information is available at www.nature.com/reprints.

Publisher's note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons license, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons license, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons license and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this license, visit <http://creativecommons.org/licenses/by/4.0/>.

© The Author(s) 2020